

UNCLASSIFIED

AD **431736**

DEFENSE DOCUMENTATION CENTER

FOR

SCIENTIFIC AND TECHNICAL INFORMATION

CAMERON STATION, ALEXANDRIA, VIRGINIA



UNCLASSIFIED

NOTICE: When government or other drawings, specifications or other data are used for any purpose other than in connection with a definitely related government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

164 845 64-10

⑤ 625200

NOLTR 63-142

①

431736

AD No.

DDC FILE COPY

TEMPERATURE-YIELD STRENGTH
CORRELATION OF THE CRATER SIZE
PRODUCED IN ALUMINUM BY THE
HYPERVELOCITY IMPACT OF
ALUMINUM SPHERES

431736

MAR 6 1964

30 AUGUST 1963

NOL

UNITED STATES NAVAL ORDNANCE LABORATORY, WHITE OAK, MARYLAND

NOLTR 63-142

3388

15 P \$1.60

7/1

0625000
UNCLASSIFIED
NOLTR 63-142

Ballistics Research Report 108

⑥ TEMPERATURE-YIELD STRENGTH CORRELATION OF THE CRATER
SIZE PRODUCED IN ALUMINUM BY THE HYPERVELOCITY
IMPACT OF ALUMINUM SPHERES

Prepared by:
R. Piacesi, R. H. Waser and V. C. D. Dawson.

ABSTRACT: An investigation was made to determine the correlation between target temperature and target yield strength for the hypervelocity impact of aluminum spheres upon semi-infinite aluminum targets. It was shown that an exact correlation does exist. In the velocity range covered in the experiment (12,700 feet per second to 21,750 feet per second) the crater volume was dependent on the -0.396 power of the yield strength. It was also observed that a transition region exists at an impact velocity of about 13,000 feet per second, such that the crater volume is not linearly dependent on the kinetic energy of the projectile, but that for velocities from 13,000 feet per second and up to at least 21,750 feet per second the crater volume is dependent on the velocity to the 1.78 power.

PUBLISHED MARCH 1964

U. S. NAVAL ORDNANCE LABORATORY
WHITE OAK, MARYLAND

1
UNCLASSIFIED

NOLTR 63-142

30 August 1963

TEMPERATURE-YIELD STRENGTH CORRELATION OF THE CRATER SIZE
PRODUCED IN ALUMINUM BY THE HYPERVELOCITY IMPACT OF ALUMINUM
SPHERES

This work was performed as a part of Polaris Long Range
Research under Task Number PR-23.

R. E. ODENING
Captain, USN
Commander

A. E. Seigel
A. E. SEIGEL
By direction

CONTENTS

	Page
LIST OF SYMBOLS.	iv
INTRODUCTION	1
EXPERIMENT	1
CONCLUSION	3

ILLUSTRATIONS

Figure	Title
1	Yield Strength Correlation
2	Crater Size Dependence on Yield Strength
3	66-Ft. Hyperballistics Range No. 2
4	A Sequence of Pictures of a 1/4-Inch Aluminum Sphere Impacting a 7075-O Aluminum Target at Room Temperature. Impact Velocity = 14,700 Ft./Sec.

REFERENCES

- (1) Ferguson, W. J., and McKinney, K. R., "The Influence of Temperature Elevation on the Penetration of Missiles in Copper Targets," NRL Report 5407, 19 Nov 1959
- (2) Allison, F. E., Becker, K. R. and Vitali, R., "Effects of Target Temperature on Hypervelocity Cratering," Fourth Hypervelocity Impact Symposium, Vol. 1, Apr 1960
- (3) Rockowitz, R., Carey, C. A., and Dignam, J. F., "Hypervelocity Impact of Heated Copper," Fifth Symposium on Hypervelocity Impact, Vol 1, Part 2, Apr 1962
- (4) Bjork, R. L., "Effects of a Meteoroid Impact on Steel and Aluminum in Space," Technical Report P-1662, Rand Corporation, Eng. Division, 16 Dec 1958

LIST OF SYMBOLS

c_o	speed of sound in the target
v_o	projectile impact velocity
v_c	volume of the crater
v_p	volume of the projectile

INTRODUCTION

A prerequisite for the complete formulation of the effects of high-velocity particles impacting on a thick target is the understanding of the basic physical processes involved. Each of the large number of variables which appear to influence the resulting crater dimensions and their interdependence must be evaluated.

Although it is generally recognized that some mechanical strength property of the target and its temperature dependence is important in the cratering process, no experiments have tied down this temperature-strength correlation. An investigation was made to determine if there is an exact correlation between the target yield strength and the target temperature.

EXPERIMENT

It has generally been known that the crater size is dependent on the mechanical strength of the target. Experiments have also been conducted demonstrating that heating the target caused larger craters to result from impacts (ref. (1)). It has also been pointed out that when the temperature is varied, anomalies in the crater dimensions appear at temperatures where anomalies occur in the strength of the target material (ref. (2)). Others have shown that a favorable graphical comparison exists between the cratering efficiency and the target tensile strength as a function of temperature (ref. (3)). The question arises then, as to whether an exact correlation in crater size exists between the target temperature and a mechanical property, such as the yield strength. For example: consider cratering in two targets of the same material but different yield strengths. If the yield strength of the two targets was made equal by raising the temperature of the higher-yield strength target, would equal size craters be obtained for a given impact?

The experiment consisted of firing 1/4-inch diameter aluminum spheres into 2-inch thick, 8-inch diameter aluminum targets. The targets were of 7075-T6, 2017-T4 and 7075-O aluminum having room temperature yield strengths of 68,500 psi, 38,500 psi and 17,000 psi, respectively. (These values were obtained from yield strength tests made on samples of the target material stock.) A range of impact velocities was covered for each of the three different targets at room temperature and the resulting craters were measured. Impacts were made on four 7075-T6 targets, two which were heated to 380°F and two to 500°F, having true yield strengths of 40,500 psi and 25,500 psi, respectively, and on one 2017-T4 target heated to 357°F having

a true yield strength of 25,500 psi. (These yield strength values were also obtained from curves constructed with data from yield strength tests made over a range of temperatures.)

The crater volume was measured with reference to the original surface using a low surface tension fluid and a hypodermic syringe. The depth was measured with a depth micrometer and the diameter was measured with an optical comparator. The correlation was made with the crater volume because of the large scatter in the depth. This scatter was due to the roughness of the craters in the more brittle 2017-T4 and 7075-T6 targets.

A log-log plot of the parameters V_c/V_p against V_0/C_0 is shown in figure 1. The room temperature constant yield strength lines indicated that the V_c/V_p was dependent on the $-.396$ power of the yield strength at constant velocity (see fig. 2) for velocities from 12,600 feet per second to at least 21,750 feet per second. An interpolation was made for the lines of constant yield strength for the heated target conditions. The experimental temperature-yield strength correlation is seen to be very good with the exception of one point for one of the 7075-T6 targets which was heated to 380°F, in which case the point is high. It should be noted that the slope of the constant yield strength lines is not 2 but 1.78, indicating that a transition region has appeared. This would mean that we have reached a region where strength effects may be starting to diminish in importance. The one low-velocity shot into the room temperature 2017-T4 target did not fall on the 1.78 slope line and therefore was assumed to be in the kinetic energy dependent region. A line of slope equal to 2 was drawn through this point to observe where the transition point might be. The transition point for the 2017-T4 target is indicated to be at 12,000 feet per second. When the point is reached where the strength effects can be ignored, the slope should be equal to 1.0 (ref. (4)) and the lines of constant yield strength should converge into only one line. In order for the lines to converge, the transition point should occur at lower velocities in the lower-yield strength targets. A line indicating the possible transition point as a function of yield strength is shown in figure 1.

It was intended to further substantiate the temperature yield strength correlation by firing more shots into heated targets and also to investigate the transition region by firing low-velocity shots into room temperature targets. However, sabot problems which depleted the supply of target material prevented a continuation of the test at the present time. It is the intention of the authors to continue this investigation more thoroughly with a new supply of target materials.


The test facility used for this program was the NOL Ballistics Range No. 2. This range is a 66-foot long, 3-foot diameter tube which can be evacuated to less than 1 mm Hg pressure and which is equipped with projectile velocity measuring instrumentation consisting of light screens and time interval counters. A Beckman-Whitley 192 high-speed framing camera and a flashtube light source were installed for this program to photograph the impact of the projectile with the test targets. A 0.500-inch two-stage light-gas gun was used to accelerate the 0.250-inch aluminum sphere projectiles to velocities up to 22,000 feet per second. Figure 3 shows the range facility setup schematically. The still camera with spark light source is associated with the velocity measuring system to provide a positive check on its operation by photographing the projectile which triggers the light screens.

For the shots in which the target was heated, a 1,000 watt electric Calrod heater was fastened to the back side of the target and temperature was monitored by making use of a thermocouple placed in a hole drilled in the target. It was experimentally determined that the temperature gradient in the target and the inaccuracy in measuring temperature amounted to no more than 3°F. Before firing, the projectiles were mounted in bore-size lexan sabots, which were stripped off and deflected as they left the muzzle of the gun. The range tube pressure in all cases was decreased to less than 2 mm Hg pressure to prevent the projectile from ablating before its impact with the target.


A sequence of impact pictures taken with the high-speed framing camera are shown in figure 4.

CONCLUSION

It is concluded that there is an exact correlation between temperature and yield strength. The crater volume is seen to be dependent on the $-.396$ power of the yield strength for impacts of aluminum spheres on semi-infinite aluminum targets in the velocity range from 12,700 feet per second to 21,750 feet per second. From a transition point at about 13,000 feet per second and up to at least 21,750 feet per second the crater volume is not dependent on the kinetic energy of the projectile but rather on the velocity to the 1.78 power, indicating that the strength effect on the cratering process may be diminishing above a velocity of 13,000 feet per second.




YIELD STRENGTH CORRELATION
FIGURE 1




CRATER SIZE DEPENDENCE ON YIELD STRENGTH

FIGURE 2




66 FT. HYPERBALLISTICS RANGE NO. 2
FIGURE 3


NOLTR 63-142



$t=0$
TIME IN MICROSECONDS



$t=1.37$



$t=2.74$



$t=9.59$



$t=13.7$



$t=17.81$



$t=26.3$



$t=31.51$



$t=52.06$

A SEQUENCE OF PICTURES OF A $\frac{1}{4}$ INCH ALUMINUM SPHERE
IMPACTING A 7075-O ALUMINUM TARGET AT ROOM
TEMPERATURE. IMPACT VELOCITY=14,700 FT./SEC.

FIGURE 4

NOLTR 63-142

Distribution

	<u>Copies</u>
Chief, Bureau of Naval Weapons	
Department of the Navy	
Washington 25, D. C.	
Attn: RMMO	1
Attn: RMGA	1
Attn: RRMA	1
Director, Special Projects	
Department of the Navy	
Washington 25, D. C.	
Attn: SP-20	4
Attn: SP-27	2
Attn: SP-272	1
Office of Naval Research	
Room 2709 - T-3	
Washington 25, D. C.	
Attn: Head, Mechanics Br.	1
Commanding Officer	
Office of Naval Research	
Branch Office, Box 39, Navy 100	
Fleet Post Office, New York, N. Y.	5
Director, DTMB	
Aerodynamics Laboratory	
Washington 7, D. C.	
Attn: Library	1
Naval Weapons Laboratory	
Dahlgren, Va.	
Attn: Library	1
Commander	
U. S. Naval Ordnance Test Station	
China Lake, Calif.	
Attn: Technical Library	1
Director	
Naval Research Laboratory	
Washington 25, D. C.	
Attn: Code 2027	1
Attn: Mr. Edward Chapin, Code 6310	1
Attn: Mr. W. Watkins	1
Attn: Mr. H. F. Swift	1

	<u>Copies</u>
Director of Intelligence Headquarters, USAF Washington 25, D. C. Attn: AFOIN-3B	1
Commander Aeronautical Systems Division Wright-Patterson Air Force Base, Ohio Attn: WCOSI-3 Attn: WCLSW-5 Attn: WCRRD Attn: Melvin L. Buck (ASRMDF-2)	2 1 3 1
Commander Air Res. & Develop. Command P. O. Box 262 Inglewood, Calif. Attn: WDTLAR	1
Chief, DASA The Pentagon Washington, D. C. Attn: Document Library	1
Headquarters Arnold Engineering Development Center (ARDC) U. S. Air Force Arnold Air Force Station, Tennessee Attn: Technical Library Attn: AEOR	1 1
Commanding Officer, Harry Diamond Laboratory Washington 25, D. C. Attn: Library Rm. 211, Bldg. 92	1
NASA George C. Marshall Space Flight Center Huntsville, Alabama Attn: M-S&M-PT (Mr. H. A. Connell) Attn: Dr. W. R. Lucas (M-SFM-M) Attn: Dr. Ernst Geissler	5 1 1
Office, Chief of Ordnance Department of the Army Washington 25, D. C. Attn: ORDTU	1

Copies

APL/JHU	
8621 Georgia Ave.	
Silver Spring, Md.	
Attn: Tech. Reports Group	2
Attn: Dr. D. Fox	1
Attn: Dr. Freeman Hill	1
Attn: Dr. L. L. Cronvich	1
Attn: Librarian	1
AVCO Manufacturing Corp.	
Research & Advanced Development Div.	
201 Lowell Street	
Wilmington, Mass.	
Attn: Dr. B. D. Henschel, Aerodynamics Section	1
AVCO Manufacturing Corp.	
Everett, Mass.	
Attn: Dr. Kantrowitz	1
General Electric Co.	
Space Vehicle & Missiles Dept.	
21 South 12th St.	
Philadelphia, Penn.	
Attn: Dr. J. Stewart	1
Attn: Dr. Otto Klima	1
Attn: Mr. E. J. Nolan	1
Attn: Mr. L. McCreight	1
Attn: Mr. T. D. Riney	1
Attn: Mr. P. R. Chernoff	1
General Electric	
Space Sciences Laboratory	
3750 "D" St.	
Philadelphia 24, Penn.	
Attn: Dr. Leo Steg	1
Scientific & Technical Information Facility	
P. O. Box 5700	
Bethesda, Maryland	
Attn: NASA Representative	5
NASA	
High Speed Flight Station	
Edwards Field, Calif.	
Attn: W. C. Williams	1

NOLTR 63-142

	<u>Copies</u>
BSD(BSRF)	
A. F. Unit Post Office	
Los Angeles 45, Calif.	2
NASA	
Langley Research Center	
Langley Field, Va.	
Attn: Librarian	1
Attn: C. H. McLellan	1
Attn: J. J. Stack	1
Attn: Adolf Busemann	1
Attn: Rodger W. Peters (Structures Res. Div.)	1
Attn: Russell Hopko, PARD	1
NASA	
Ames Research Center	
Moffett Field, Calif.	
Attn: Librarian	1
NASA	
Lewis Research Center	
21000 Brookpark Rd.	
Cleveland, Ohio	
Attn: Chief, Propulsion Aerodynamics Div.	1
Attn: Mr. George Mandel, Chief, Library	2
Office of the Assistant	
Secretary of Defense (R&D)	
Room 3E1041, The Pentagon	
Washington 25, D. C.	
Attn: Library (Technical)	1
Research and Development Board	
Room 3D1041, The Pentagon	
Washington 25, D. C.	
Attn: Library	2
DFC Headquarters	
Cameron Station	
Arlington, Va.	20
Commander, Pacific Missile Range	
Point Mugu, Calif.	
Attn: Technical Library	1
Commanding General	
Aberdeen Proving Ground, Md.	
Attn: Technical Info. Br.	1
Attn: Ballistics Research Laboratories	1

	<u>Copies</u>
Los Alamos Scientific Laboratory P. O. Box 1663 Los Alamos, New Mexico Attn: Dr. Donald F. MacMillan N-1 Group Leader	1
Institute for Defense Analyses Advanced Research Projects Agency Washington 25, D. C. Attn: W. G. May General Sciences Branch	1
Kaman Aircraft Corporation Nuclear Division Colorado Springs, Colorado Attn: Dr. A. P. Bridges	1
U. S. Atomic Energy Commission P. O. Box 62 Oak Ridge, Tennessee Attn: TRI:NLP:ATD:10-7	1
Sandia Corporation Livermore Laboratory P. O. Box 969 Livermore, Calif.	1
United Aircraft Corporation Research Laboratories East Hartford 8, Conn. Attn: Mr. H. J. Charette Attn: Mr. H. Taylor	1 1
Sandia Corporation Sandia Base Albuquerque, N. Mexico Attn: Mr. Alan Pope	1
Defense Metals Information Center Battelle Memorial Institute 505 King Avenue Columbus 1, Ohio	1
Commanding General Army Rocket and Guided Missile Agency Redstone Arsenal, Alabama Attn: John Morrow	1

	<u>Copies</u>
Aerospace Corporation El Segundo, Calif. Attn: Dr. Bitondo	1
Lockheed Aircraft Corp. Missiles and Space Div. P. O. Box 504 Sunnyvale, Calif. Attn: Dr. L. H. Wilson	1
Lockheed Aircraft Corp. Research Lab. Palo Alto, California Attn: W. Griffith	1
Atomic Energy Commission Engineering Development Branch Division of Reactor Development Headquarters, US AEC Washington 25, D. C. Attn: Mr. J. M. Simmons Attn: Mr. J. Conners	1 1
University of California Lawrence Radiation Laboratory P. O. Box 808 Livermore, Calif. Attn: Mr. W. M. Wells, Propulsion Div. Attn: Mr. Carl Kline	1 1
Oak Ridge National Laboratory P. O. Box E Oak Ridge, Tenn. Attn: Mr. W. D. Manly	1
General Applied Sciences Laboratories, Inc. Merrick and Stewart Avenues East Meadow, New York Attn: Mr. Robert Byrne	1
Jet Propulsion Laboratory 4800 Oak Grove Drive Pasadena 3, Calif. Attn: I. R. Kowlan, Chief, Reports Group Attn: Dr. L. Jaffee	1 2

	<u>Copies</u>
National Bureau of Standards Washington 25, D. C. Attn: Dr. Galen B. Schubauer	1
Cornell Aeronautical Laboratory 4455 Genesee Street Buffalo, N. Y. Attn: Dr. Gordon Hall	1
Dept. of Mechanical Engineering University of Delaware Newark, Delaware Attn: Dr. James P. Hartnett	1
General Electric Company Missile and Space Vehicle Dept. 3198 Chestnut Street Philadelphia, Pennsylvania Attn: Jerome Persh	1
Professor Ting Yi Li Aerospace Engineering Department University of Cincinnati College of Engineering Cincinnati 21, Ohio	1
Hayes International Corp. P. O. Box 2287 Birmingham, Alabama Attn: J. F. Hawk Dept. 514	1
Carnegie Institute of Technology Department of Physics Pittsburgh 13, Pennsylvania Attn: Dr. E. M. Pugh	1
General Motors Corporation GM Defense Research Laboratories Aerospace Operations Dept. Santa Barbara, California Attn: C. J. Maiden	1
Massachusetts Institute of Technology Lincoln Laboratory Cambridge 39, Massachusetts Attn: Technical Library	1

NOLTR 63-142

	<u>Copies</u>
Picatinny Arsenal Dover, New Jersey Attn: Library	1
Stanford Research Institute Menlo Park, California Attn: Technical Library	1
University of Utah Experimental Research Laboratory Salt Lake City, Utah Attn: Technical Library	1
Rand Corporation 1700 Main Street Santa Monica, California Attn: R. L Bjork	1

CATALOGING INFORMATION FOR LIBRARY USE

BIBLIOGRAPHIC INFORMATION			
DESCRIPTORS	CODES	DESCRIPTORS	CODES
SOURCE	NOL technical report	SECURITY CLASSIFICATION AND CODE COUNT	Unclassified - 20
REPORT NUMBER	63-142	CIRCULATION LIMITATION	U920
REPORT DATE	30 August 1963	CIRCULATION LIMITATION OR BIBLIOGRAPHIC	
		BIBLIOGRAPHIC SUPPL., VOL., ETC.)	


SUBJECT ANALYSIS OF REPORT

DESCRIPTORS	CODES	DESCRIPTORS	CODES
Hypervelocity	HYPV	Volume	VOLU
Impact	IMPC	Dependence	DEPN
Crater	CRAT	Variations	VART
Size	SIZE	Heat	HEAT
Temperature	TEMP	Mechanical	MECA
Yield	YIEL	Target (properties)	TARCP
Strength	STRN	Physics	PHYS
Correlation	CORA	Aeroballistics	AERB
Alumina	ALUM		
Targets	TARG		
Spheres	SPHE		
Velocities	VELC		

<p>1. Impact, High speed</p> <p>2. Penetration - Spheres</p> <p>3. Penetration - Aluminum</p> <p>I. Piacesi, Robert</p> <p>II. Series</p> <p>III. Project</p> <p>IV. Project</p> <p>Abstract card is unclassified.</p>	<p>Naval Ordnance Laboratory, White Oak, Md. (NOL technical report 63-142) TEMPERATURE-YIELD STRENGTH CORRELATION OF THE CRATER SIZE PRODUCED IN ALUMINUM BY THE HYPERVELOCITY IMPACT OF ALUMINUM SPHERES (U), by R. Piacesi and others. 30 Aug. 1963. 3p. illus. (Ballistics research report 108) BuWeps task PR-23. UNCLASSIFIED</p> <p>An investigation was made to determine the correlation between target temperature and target yield strength for the hypervelocity impact of aluminum spheres upon semi-infinite aluminum targets. It was shown that an exact correlation does exist. The experiment demonstrated that for velocities from 12,700 feet per second and up to at least 21,750 feet per second the crater volume is dependent on the -.396 power of the yield strength.</p>	<p>1. Impact, High speed</p> <p>2. Penetration - Spheres</p> <p>3. Penetration - Aluminum</p> <p>I. Piacesi, Robert</p> <p>II. Series</p> <p>III. Project</p> <p>IV. Project</p> <p>Abstract card is unclassified.</p>	<p>Naval Ordnance Laboratory, White Oak, Md. (NOL technical report 63-142) TEMPERATURE-YIELD STRENGTH CORRELATION OF THE CRATER SIZE PRODUCED IN ALUMINUM BY THE HYPERVELOCITY IMPACT OF ALUMINUM SPHERES (U), by R. Piacesi and others. 30 Aug. 1963. 3p. illus. (Ballistics research report 108) BuWeps task PR-23. UNCLASSIFIED</p> <p>An investigation was made to determine the correlation between target temperature and target yield strength for the hypervelocity impact of aluminum spheres upon semi-infinite aluminum targets. It was shown that an exact correlation does exist. The experiment demonstrated that for velocities from 12,700 feet per second and up to at least 21,750 feet per second the crater volume is dependent on the -.396 power of the yield strength.</p>
<p>1. Impact, High speed</p> <p>2. Penetration - Spheres</p> <p>3. Penetration - Aluminum</p> <p>I. Piacesi, Robert</p> <p>II. Series</p> <p>III. Project</p> <p>IV. Project</p> <p>Abstract card is unclassified.</p>	<p>Naval Ordnance Laboratory, White Oak, Md. (NOL technical report 63-142) TEMPERATURE-YIELD STRENGTH CORRELATION OF THE CRATER SIZE PRODUCED IN ALUMINUM BY THE HYPERVELOCITY IMPACT OF ALUMINUM SPHERES (U), by R. Piacesi and others. 30 Aug. 1963. 3p. illus. (Ballistics research report 108) BuWeps task PR-23. UNCLASSIFIED</p> <p>An investigation was made to determine the correlation between target temperature and target yield strength for the hypervelocity impact of aluminum spheres upon semi-infinite aluminum targets. It was shown that an exact correlation does exist. The experiment demonstrated that for velocities from 12,700 feet per second and up to at least 21,750 feet per second the crater volume is dependent on the -.396 power of the yield strength.</p>	<p>1. Impact, High speed</p> <p>2. Penetration - Spheres</p> <p>3. Penetration - Aluminum</p> <p>I. Piacesi, Robert</p> <p>II. Series</p> <p>III. Project</p> <p>IV. Project</p> <p>Abstract card is unclassified.</p>	<p>Naval Ordnance Laboratory, White Oak, Md. (NOL technical report 63-142) TEMPERATURE-YIELD STRENGTH CORRELATION OF THE CRATER SIZE PRODUCED IN ALUMINUM BY THE HYPERVELOCITY IMPACT OF ALUMINUM SPHERES (U), by R. Piacesi and others. 30 Aug. 1963. 3p. illus. (Ballistics research report 108) BuWeps task PR-23. UNCLASSIFIED</p> <p>An investigation was made to determine the correlation between target temperature and target yield strength for the hypervelocity impact of aluminum spheres upon semi-infinite aluminum targets. It was shown that an exact correlation does exist. The experiment demonstrated that for velocities from 12,700 feet per second and up to at least 21,750 feet per second the crater volume is dependent on the -.396 power of the yield strength.</p>

<p>Naval Ordnance Laboratory, White Oak, Md. (NOL technical report 63-142) TEMPERATURE-YIELD STRENGTH CORRELATION OF THE CRATER SIZE PRODUCED IN ALUMINUM BY THE HYPERVELOCITY IMPACT OF ALUMINUM SPHERES (U), by R. Piacesi and others. 30 Aug. 1963. Sp. illus. (Ballistics research report 108) BuWeps task PR-23. UNCLASSIFIED</p> <p>An investigation was made to determine the correlation between target temperature and target yield strength for the hypervelocity impact of aluminum spheres upon semi-infinite aluminum targets. It was shown that an exact correlation does exist. The experiment dem- onstrated that for velocities from 12,700 feet per second and up to at least 21,750 feet per second the crater volume is dependent on the -.396 power of the yield strength.</p>	<ol style="list-style-type: none"> 1. Impact, High speed 2. Penetration - Spheres 3. Penetration - Aluminum <ol style="list-style-type: none"> I. Title II. Piacesi, Robert III. Series IV. Project <p>Abstract card is unclassified.</p>
<p>Naval Ordnance Laboratory, White Oak, Md. (NOL technical report 63-142) TEMPERATURE-YIELD STRENGTH CORRELATION OF THE CRATER SIZE PRODUCED IN ALUMINUM BY THE HYPERVELOCITY IMPACT OF ALUMINUM SPHERES (U), by R. Piacesi and others. 30 Aug. 1963. Sp. illus. (Ballistics research report 108) BuWeps task PR-23. UNCLASSIFIED</p> <p>An investigation was made to determine the correlation between target temperature and target yield strength for the hypervelocity impact of aluminum spheres upon semi-infinite aluminum targets. It was shown that an exact correlation does exist. The experiment dem- onstrated that for velocities from 12,700 feet per second and up to at least 21,750 feet per second the crater volume is dependent on the -.396 power of the yield strength.</p>	<ol style="list-style-type: none"> 1. Impact, High speed 2. Penetration - Spheres 3. Penetration - Aluminum <ol style="list-style-type: none"> I. Title II. Piacesi, Robert III. Series IV. Project <p>Abstract card is unclassified.</p>
<p>Naval Ordnance Laboratory, White Oak, Md. (NOL technical report 63-142) TEMPERATURE-YIELD STRENGTH CORRELATION OF THE CRATER SIZE PRODUCED IN ALUMINUM BY THE HYPERVELOCITY IMPACT OF ALUMINUM SPHERES (U), by R. Piacesi and others. 30 Aug. 1963. Sp. illus. (Ballistics research report 108) BuWeps task PR-23. UNCLASSIFIED</p> <p>An investigation was made to determine the correlation between target temperature and target yield strength for the hypervelocity impact of aluminum spheres upon semi-infinite aluminum targets. It was shown that an exact correlation does exist. The experiment dem- onstrated that for velocities from 12,700 feet per second and up to at least 21,750 feet per second the crater volume is dependent on the -.396 power of the yield strength.</p>	<ol style="list-style-type: none"> 1. Impact, High speed 2. Penetration - Spheres 3. Penetration - Aluminum <ol style="list-style-type: none"> I. Title II. Piacesi, Robert III. Series IV. Project <p>Abstract card is unclassified.</p>
<p>Naval Ordnance Laboratory, White Oak, Md. (NOL technical report 63-142) TEMPERATURE-YIELD STRENGTH CORRELATION OF THE CRATER SIZE PRODUCED IN ALUMINUM BY THE HYPERVELOCITY IMPACT OF ALUMINUM SPHERES (U), by R. Piacesi and others. 30 Aug. 1963. Sp. illus. (Ballistics research report 108) BuWeps task PR-23. UNCLASSIFIED</p> <p>An investigation was made to determine the correlation between target temperature and target yield strength for the hypervelocity impact of aluminum spheres upon semi-infinite aluminum targets. It was shown that an exact correlation does exist. The experiment dem- onstrated that for velocities from 12,700 feet per second and up to at least 21,750 feet per second the crater volume is dependent on the -.396 power of the yield strength.</p>	<ol style="list-style-type: none"> 1. Impact, High speed 2. Penetration - Spheres 3. Penetration - Aluminum <ol style="list-style-type: none"> I. Title II. Piacesi, Robert III. Series IV. Project <p>Abstract card is unclassified.</p>

UNCLASSIFIED



UNCLASSIFIED